



Tekwani Applications Limited

77 Northover Rd, Westbury on Trym
Bristol BS9 3LQ, United Kingdom
tel +44 (0)117 9501710
e-mail wax@trycut.co.uk

TRYCUT

Easy Cutting Plastic / Wax

www.trycut.co.uk



TRYCUT - TECHNICAL DATA SHEET

1: Composition

A mixture of petroleum derived hydrocarbon waxes, resins and polymers plus the incorporation of colouring agent dyes.

There are no hazardous ingredients and the wax conforms to RoHS Directive (2011/65/EU) in terms of restrictive substances referred to in Article 4(1).

2: Physical and Chemical properties

Physical State	Waxy solid
Colour	Blue
Boiling Point / Range (°C)	Above 300
Melting point / Range (°C)	105-115 (ring and ball)
Viscosity	170 (°C) - 1000 cps 150 (°C) - 1600 cps 130 (°C) - 2750 cps
Hardness (Shore D)	55
Ash Content %	< 0.03
Flash Point (closed : °C)	Above 280
Relative Density (@ 20 °C)	0.94 Kg / litre
Solubility in water	Insoluble

3: Manufacture

Trycut wax is manufactured in the United Kingdom from materials sourced in the United Kingdom.

Classification code for export – 3404 9000
Trycut waxes are of UK/ EU origin

Although the information contained in this data sheet is presented in good faith and to the best of Tekwani Applications Limited's, knowledge and experience, it is made without any warranty or guarantee whatsoever.